


CLASSIFICATION REPORT REACTION TO FIRE



NUMBER	251.Z.2311.063.EN.01	Work sheet: 22301297
DATE OF ISSUE	November 13 th , 2023	
PAGE	The report consists of 5 pages consecutively numbered, an annex of 2 pages.	
TEST SPECIMEN	Type: WALLS AND CEILINGS COVERINGS Reference: "FBA1 NO FIRE FONDO PU TRANSPARENTE + FGA11 NO FIRE ACABADO PU TRANSP OP70 G"	
CONCERNING TO	CLASSIFICATION OF FIRE PERFORMANCE OF CONSTRUCTION PRODUCTS AND BUILDING ELEMENTS. CLASSIFICATION USING DATA OBTAINED IN REACTION TO FIRE TESTS ACCORDING TO STANDARD EN 13501-1:2018.	
APPLICANT	IVM CHEMICALS SRL. DIVISION: MILES VIALE DELLA STAZIONE, 3 27020 PARONA (PV) - ITALY	
DATE/S OF TEST	Reception of specimens: 11/07/23 and 31/08/23 Beginning of test: 17/07/2023 End of test: 05/10/2023	

AUTHORIZED SIGNATORIES

Signed.: Ms. Raquel Cánovas Ruiz
Technician Fire Lab

Signed.: Mr. Stephane García Malpartida
Head of Section - Fire Laboratory

Document digitally signed by a legal electronic signature.

The test sample object of this report will remain in AIDIMME for a period of thirty days from the date of issuance thereof. After this period, the sample will be destroyed, therefore any verification that the client wishes to exercise, must be carried out within these limits.

CONTENTS

1. INTRODUCTION 3

2. PRODUCT DATA CLASSIFIED 3

 2.1 Inspection prior to test by the laboratory..... 3

 2.2. Description and Identification of the test item provided by the customer. 3

3. TEST REPORTS SUPPORTING THE CLASSIFICATION 3

4. TEST RESULTS SUPPORTING THE CLASSIFICATION..... 4

5. CLASSIFICATION AND FIELD OF APPLICATION..... 5

 5.1. Classification..... 5

 5.2. Field of application 5

6. LIMITATIONS 5

ANNEX A1

1. INTRODUCTION

This classification report defines the classification assigned to the product described in paragraph 2, in accordance with the procedures pointed in the **EN 13501-1:2018** "Fire classification of construction products and building elements – Part 1: Classification using data from reaction to fire tests".

2. PRODUCT DATA CLASSIFIED

2.1 Inspection prior to test by the laboratory.

Test SBI and little burner

Samples corresponding to transparent varnished applied on MDF support. The sample is labelled in AIDIMME with the reference: **2307080-03**.

2.2. Description and Identification of the test item provided by the customer.

Samples corresponding to transparent varnish applied on MDF board with a thickness of 19 mm and a density of 760 Kg/m³ (classified as B-s2,d0, according to UNE EN 13501-1). The application process consists of two layers of 150 g/m² each one of product **FBA1 NO FIRE Fondo PU trasparente**, catalysed 50% with FNB1 Hardener, presenting an approximate density of (1111 ± 0.01) Kg/m³, transparent and matte appearance, with a drying time between layers of the 24 hours. Subsequently, a layer of 120 g/m² of **FGA11 NO FIRE Acabado PU Transparente OP70 Gloss**, catalysed 50% with FNB1 Hardener which has an approximate density of (1020 ± 0.01) Kg/m³, transparent and semi-gloss appearance, all this according to the information provided by the customer and referenced as:

- "FBA1 NO FIRE FONDO PU TRANSPARENTE + FGA11 NO FIRE ACABADO PU TRANSP OP70 G"
(Ref. AIDIMME: 2307080-03)

3. TEST REPORTS SUPPORTING THE CLASSIFICATION

Laboratory	Company/Customer	Test report reference	Test method
ENSATEC	IVM CHEMICALS SRL. DIVISION: MILESI	251.I.2311.063.ES.01	UNE-EN 13823:21+A1:2023
AIDIMME	IVM CHEMICALS SRL. DIVISION: MILESI	251.I.2311.063.ES.01	UNE-EN ISO 11925-2:21

4. TEST RESULTS SUPPORTING THE CLASSIFICATION

Test method	Parameter	Númer of test	Results	
			Average of continuous parameter (m)	Compliance with parameters
UNE EN ISO 11925-2:21 (little burner) “FBA1 NO FIRE FONDO PU TRANSPARENTE + FGA11 NO FIRE ACABADO PU TRANSP OP70 G” Ref. AIDIMME : 2307080-03	$F_s \leq 150\text{mm}$	12	Not applicable	Compliant
	Ignition of the filter paper		Not applicable	Compliant
UNE-EN 13823:21+A1:2023 (SBI) “FBA1 NO FIRE FONDO PU TRANSPARENTE + FGA11 NO FIRE ACABADO PU TRANSP OP70 G” Ref. AIDIMME : 2307080-03	FIGRA _{0,2MJ} (W/s)	3	46.50	Compliant
	FIGRA _{0,4MJ} (W/s)		42.56	Compliant
	THR _{600s} (MJ)		3.71	Compliant
	TSP _{600s} (m ²)		42.88	Compliant
	SMOGRA (m ² /s ²)		4.93	Compliant
	LFS (Y/N)		Not applicable	Compliant
	Falling of flaming droptles/particles (Y/N)		Not applicable	Compliant

Note 1: Test subcontracted to an external laboratory accredited by ENAC 288/LE 634 accreditation.

Test uncertainty

The uncertainty for the FIGRA_{0,2MJ} and THR_{600s} parameters is 25% and 2% respectively.

The uncertainty for the SMOGRA y TSP_{600s} parameters is 10% and 5% respectively.

5. CLASSIFICATION AND FIELD OF APPLICATION

5.1. Classification.

Therefore, according to standard **EN 13501-1:2018**, and view of the test results and the classification criteria are attached at the Annex (table 1 of the mentioned standard), the sample described in section 2.2 of this report, all according to the information provided by the customer and referenced by the same **“FBA1 NO FIRE FONDO PU TRANSPARENTE + FGA11 NO FIRE ACABADO PU TRANSP OP70 G”** is classified in relation to the fire behavior as:

Reaction to fire	Smoke production	Drops in flame
B	s1	d0

5.2. Field of application

The classified product is defined for the use in walls and ceilings coverings.

5.2.1 Product parameters

- Composition: MDF board (reaction to fire B-s2,d0) on which a process is applied (see description section 2.2). Variations not allowed.
- Color: Transparent. Variations not allowed.
- Mass per area (painting): 150 g/m² per layer (2 layers) of FBA1 NO FIRE Fondo PU transparente and 120 g/m² of FGA11 NO FIRE Acabado PU Transaprente OP70 Gloss. Variations not allowed.
- Support: Applications on any substrate with a density equal or higher to 570 Kg/m³ with a minimum thickness of 19 mm and reaction to fire B-s2,d0 or better.

5.2.2 End-use application

- Joins: Vertical and horizontal joins are not allowed.
- Substrate: The product is mounted on any inert substrate with density equal or higher to 652.5 Kg/m³, with a minimum thickness of (11 ± 2) mm and fire reaction classification A2-s1,d0 or better.

6. LIMITATIONS

The result of this report only refers to the products described in paragraph 2 thereof.

This document does not represent any type approval or certification of the product.

The duration of the validity of this classification report is subject to applicable law at the time of issue.

ANNEX**Table 1 - Classes of behaviour to fire reaction for construction products excluding floor coverings and thermal insulating products for linear pipes according to standard UNE EN 13501-1:2019**

Class	Test method (s)	Classification criteria	Additional declaration required
A1	UNE-EN-ISO 1182 ^a and	$\Delta T \leq 30^{\circ}\text{C}$; and $\Delta m \leq 50\%$; and $t_f = 0$ (that is, no sustained flaming)	-
	UNE-EN-ISO 1716	$\text{PCS} \leq 2,0 \text{ MJ/kg}^a$ and $\text{PCS} \leq 2,0 \text{ MJ/kg}^{b,y,c}$ and $\text{PCS} \leq 1,4 \text{ MJ/m}^2^d$ and $\text{PCS} \leq 2,0 \text{ MJ/kg}^e$	-
A2	UNE-EN-ISO 1182 ^a or	$\Delta T \leq 50^{\circ}\text{C}$; and $\Delta m \leq 50\%$; and $t_f \leq 20\text{s}$	-
	UNE-EN-ISO 1716 and	$\text{PCS} \leq 3,0 \text{ MJ/kg}^a$; and $\text{PCS} \leq 4,0 \text{ MJ/m}^2^d$ and $\text{PCS} \leq 4,0 \text{ MJ/m}^2^d$ and $\text{PCS} \leq 3,0 \text{ MJ/kg}^e$	-
	UNE-EN 13823 (SBI)	$\text{FIGRA}_{0,2 \text{ MJ}} \leq 120 \text{ W/s}$; and $\text{LFS} < \text{sample edge}$; and $\text{THR}_{600\text{s}} \leq 7,5 \text{ MJ}$	Smoke production ^f and flamming drops/particles ^g
B	UNE-EN 13823 and	$\text{FIGRA}_{0,2 \text{ MJ}} \leq 120 \text{ W/s}$ and $\text{LFS} < \text{sample edge}$; and $\text{THR}_{600\text{s}} \leq 7,5 \text{ MJ}$	Smoke production ^f and flamming drops/particles ^g
	UNE-EN-ISO 11925-2 ⁱ Exposure = 30s	$F_s \leq 150\text{mm}$ in 60s	
C	UNE-EN 13823 and	$\text{FIGRA}_{0,4 \text{ MJ}} \leq 250 \text{ W/s}$ and $\text{LFS} < \text{sample edge}$; and $\text{THR}_{600\text{s}} \leq 15 \text{ MJ}$	Smoke production ^f and flamming drops/particles ^g
	UNE-EN-ISO 11925-2 ⁱ Exposure = 30s	$F_s \leq 150\text{mm}$ in 60s	
D	UNE-EN 13823 ^y	$\text{FIGRA}_{0,4 \text{ MJ}} \leq 750 \text{ W/s}^{-1}$	Smoke production ^f and flamming drops/particles ^g
	UNE-EN-ISO 11925-2 ⁱ Exposure = 30s	$F_s \leq 150\text{mm}$ in 60s	
E	UNE-EN-ISO 11925-2 ⁱ Exposure = 15s	$F_s \leq 150\text{mm}$ in 20s	Flamming drops/particles ^h
F	UNE-EN-ISO 11925-2 ⁱ Exposure = 15s	$F_s > 150\text{mm}$ in 20s	

a For homogeneous products and substantial components of heterogeneous products.

b For any non-substantial external component of heterogeneous products

c Alternatively, for any non-substantial external component having a $\text{PCS} \leq 2,0 \text{ MJ/m}^2$, as long as the product meets the following criteria Standard UNE-EN 13823 (SBI): $\text{FIGRA} \leq 20 \text{ W/s}$, and $\text{LFS} < \text{sample margin}$; and $\text{THR}_{600\text{s}} \leq 4,0 \text{ MJ}$ y s_1 ; and d_0 .

d For any internal non-substantial internal component of heterogeneous products.

e For the product as a whole

f $s_1 = \text{SMOGRA} \leq 30\text{m}^2/\text{s}^2$ and $\text{TSP}_{600\text{s}} \leq 50\text{m}^2$; $s_2 = \text{SMOGRA} \leq 180\text{m}^2/\text{s}^2$ and $\text{TSP}_{600\text{s}} \leq 200\text{m}^2$; $s_3 = \text{neither } s_1 \text{ nor } s_2$

g $d_0 = \text{No flaming droplets and particles in EN 13823 (SBI) in 600s}$

$d_1 = \text{No flaming droplets and particles for more than 10s in UNE-EN 13823 (SBI) in 600,}$

$d_2 = \text{neither } d_0 \text{ nor } d_1. \text{ The ignition of the paper in UNE EN ISO 11925-2 determines a classification } d_2.$

h Success = no ignition of the paper (without classification); Fail = ignition of the paper (classification d_2)

i Under conditions of surface flame attack and, if suitable for end conditions of product use, of edge flame attack

The results of this/these test/s only refers to the object/s tested.

This document may not be partly reproduced without the express authorization of AIDIMME

As stated in the document "**General Test Conditions**", accepted by signing the work plan, it is stated in paragraph 14:

When a declaration of conformity or classification is required, the decision rule to be applied shall follow the requirements of ILAC-G8:09/2019, in the following order (and shall be stated in the test report):

- Stated in the standard or applicable regulation.
- Agreed with the customer (within the possible options).
- If these requirements are not available, a binary statement (PASS/FAIL) shall be made for a simple Acceptance Rule, without considering the measurement uncertainty (Maximum probability of acceptance/false rejection: 50%).

In this case, the classification is made by binary statement (Compliance/Non-compliance) of the test parameters, for a simple Acceptance Rule, without taking into account the measurement uncertainty, in order to establish decision rules in the declaration of conformity. (Maximum probability of acceptance/false rejection: 50%, which **does not imply** that the probability associated with the present classification reaches this value).